

PRODUCT SPECIFICATION

L1023DEP

1.0 BASE FABRIC

1.1	Base Fabric Weight	5.08	oz/yd ²	173	g/m ²
1.2	Fiber / Style	Polyester / Knit			

2.0 COATED FABRIC

2.1	Total Weight	23 ±2	oz/yd ²	782 ±68	g/m ²
2.2	Thickness	30 ±5	mils	0.76 ±0.13	mm
2.3	Coating Type	Urethane			
2.4	Coating Distribution	60/40			
2.5	Sealing Properties	<input checked="" type="checkbox"/>	Dielectric	<input checked="" type="checkbox"/>	Thermal

3.0 MATERIAL PROPERTIES

	<u>Standard</u>	<u>Metric</u>	ASTM TEST METHODS
3.1 Tensile Strength, Grab			
Warp	350 lbs	1,560 N	D751-A
Fill	300 lbs	1,330 N	
3.2 Tensile Strength, 1" Strip			
Warp	240 lbs	1,070 N	D751-B
Fill	200 lbs	890 N	
3.3 Tear Strength, Tongue			
Warp	160 lbs	712 N	D751-B (mod)
Fill	160 lbs	712 N	
3.4 Puncture, Screwdriver	75 lbs	334 N	D751
3.5 Puncture, Ball	500 lbs	2,220 N	D751
3.6 Hydrostatic Resistance	400 psi	2.8 MPa	D751-A
3.7 Ply Adhesion	35 lbs/2 in	155 N/5 cm	D751 (mod)
3.8 Adhesion Thermal	45 lbs/in	79 N/cm	D751
3.9 Low Temp	-65 °F	-54 °C	D2136
3.10 High Temp, Cont/Interm.	160 / 180 °F	71 / 82 °C	D1204
3.11 Abrasion Resistance (Wheel H18 / 1 kg)	5,000 cycles	5,000 cycles	D3884

COMMENTS: Hydraulic conductivity = 1×10^{-6} cm/sec (max)

A variety of standard widths and colors are available. Contact Cooley Engineered Membranes for details.

The information contained herein or that is supplied by us, or on our behalf, is based upon data obtained through our own research and is considered accurate. However, No Warranty is expressed or implied regarding the accuracy of this data, the results obtained from the use thereof, or that any such use will not infringe upon any patent. This information is furnished upon the condition that the person receiving it shall evaluate its suitability for the specific application.